GENTRAL FAX GENTER

Application No. 10/743,386 Amendment dated Reply to Office Action of June 12, 2006 SEP 1 2 2008

Docket No.: 21581-00313-US

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings of claims in the application:

Please cancel claims 2, 8, 9, 12 and 15 without prejudice or disclaimer

1. (Currently Amended) A chemical conversion coating agent comprising: at least one kind selected from the group consisting of zirconium, titanium and hafnium; fluorine; and

a water-soluble resin,

wherein said water-soluble resin has, in at least a part thereof, a constituent unit expressed by the chemical formula (1):

$$\begin{array}{c} \leftarrow \text{CH}_2 - \text{CH} \rightarrow \\ \text{NH}_2 \end{array} (1)$$

and/or the chemical formula (2):

$$\begin{array}{c}
-\left(-CH_2-CH_{-}\right) \\
CH_2 \\
NH_2
\end{array}$$

and, wherein the water-soluble resin is a polyvinylamine resin or a polyallylamine resin.

- 2. (Canceled)
- 3. (Previously presented) The chemical conversion coating agent according to Claim 1,

wherein the water-soluble resin has a molecular weight of 500 to 500000, and a content of the water-soluble resin in the chemical conversion coating agent is 5 to 5000 ppm.

Application No. 10/743,386 Amendment dated Reply to Office Action of June 12, 2006 Docket No.: 21581-00313-US

4. (Previously presented) The chemical conversion coating agent according to Claim 1, containing

1 to 5000 ppm of at least one kind of a chemical conversion reaction accelerator selected from the group consisting of nitrite ion, nitro group-containing compounds, hydroxylamine sulfate, persulfate ion, sulfite ion, hyposulfite ion, peroxides, iron (III) ion, citric acid iron compounds, bromate ion, perchlorinate ion, chlorate ion, chlorate ion, as well as ascorbic acid, citric acid, tartaric acid, malonic acid, succinic acid and salts thereof.

5. (Previously presented) The chemical conversion coating agent according to Claim 1,

wherein the at least one kind selected from the group consisting of zirconium, titanium and hafnium has a content of 20 to 10000 ppm in terms of metal, and the chemical conversion coating agent has a pH of 1.5 to 6.5.

- 6. (Withdrawn) A surface-treated metal comprising a chemical conversion coat formed by the chemical conversion coating agent according to Claim 1.
- 7. (Withdrawn) The surface-treated metal according to Claim 6, wherein the chemical conversion coat has a coat amount of 0.1 to 500 mg/m² in a total amount of metals contained in the chemical conversion coating agent.
 - 8. (Canceled)
 - 9. (Canceled)

Application No. 10/743,386 Amendment dated Reply to Office Action of June 12, 2006 Docket No.: 21581-00313-US

10. (Previously presented) The chemical conversion coating agent according to Claim3, containing

1 to 5000 ppm of at least one kind of a chemical conversion reaction accelerator selected from the group consisting of nitrite ion, nitro group-containing compounds, hydroxylamine sulfate, persulfate ion, sulfite ion, hyposulfite ion, peroxides, iron (III) ion, citric acid iron compounds, bromate ion, perchlorinate ion, chlorate ion, chlorite ion, as well as ascorbic acid, citric acid, tartaric acid, malonic acid, succinic acid and salts thereof.

11. (Previously presented) The chemical conversion coating agent according to Claim 8, containing

1 to 5000 ppm of at least one kind of a chemical conversion reaction accelerator selected from the group consisting of nitrite ion, nitro group-containing compounds, hydroxylamine sulfate, persulfate ion, sulfite ion, hyposulfite ion, peroxides, iron (III) ion, citric acid iron compounds, bromate ion, perchlorinate ion, chlorate ion, chlorate ion, as well as ascorbic acid, citric acid, tartaric acid, malonic acid, succinic acid and salts thereof.

12. (Canceled)

4,

13. (Previously presented) The chemical conversion coating agent according to Claim 3,

wherein the at least one kind selected from the group consisting of zirconium, titanium and hafnium has a content of 20 to 10000 ppm in terms of metal, and the chemical conversion coating agent has a pH of 1.5 to 6.5.

14. (Previously presented) The chemical conversion coating agent according to Claim

wherein the at least one kind selected from the group consisting of zirconium, titanium and hafnium has a content of 20 to 10000 ppm in terms of metal, and the chemical conversion coating agent has a pH of 1.5 to 6.5.

Docket No.: 21581-00313-US

Application No. 10/743,386 Amendment dated Reply to Office Action of June 12, 2006

- 15. (Canceled)
- 16. (Withdrawn) A surface-treated metal comprising a chemical conversion coat formed by the chemical conversion coating agent according to Claim 3.
- 17. (Withdrawn) A surface-treated metal comprising a chemical conversion coat formed by the chemical conversion coating agent according to Claim 4.
- 18. (Withdrawn) A surface-treated metal comprising a chemical conversion coat formed by the chemical conversion coating agent according to Claim 5.
- 19. (Previously presented) The chemical conversion coating agent according to Claim9,

wherein the at least one kind selected from the group consisting of zirconium, titanium and hafnium has a content of 20 to 10000 ppm in terms of metal, and the chemical conversion coating agent has a pH of 1.5 to 6.5.

20. (Previously presented) The chemical conversion coating agent according to Claim 10.

wherein the at least one kind selected from the group consisting of zirconium, titanium and hafnium has a content of 20 to 10000 ppm in terms of metal, and the chemical conversion coating agent has a pH of 1.5 to 6.5.

21. (New) The chemical conversion coating agent according to claim 1, wherein a polyvinylamine resin or a polyallylamine resin has a molecular weight of 500 to 500000. Application No. 10/743,386 Amendment dated Reply to Office Action of June 12, 2006 Docket No.: 21581-00313-US

- 22. (New) The chemical conversion coating agent according to claim 1, wherein the water-soluble resin is a polyvinylamine resin having a molecular weight of 500 to 500000.
 - 23. (New) The chemical conversion coating agent according to claim 1, wherein the water-soluble resin is a polyallylamine resin.